



## Product information

# TEADIT TF 1580

### Description:

TEADIT **TF 1580** is a structured PTFE - Gasket - Sheet manufactured by a unique process which provides a high level of fibrillation to overcome the creep relaxation and cold flow problems associated with normal (skived or moulded) PTFE sheets. TEADIT **TF1580** is produced from virgin PTFE resin filled with Barium Sulfate.

### Advantages:



- Universal gasket sheet for all applications. It is suitable for all types of flanges, nearly all media, a broad temperature range and even for applications with the toughest demands on purity. It is inherently clean and non-toxic.
- TEADIT **TF 1580** is suitable for service with a wide variety of aggressive fluids, including hydrocarbons, moderate acids and strong caustics, solvents, water, steam, hydrogen-peroxide, refrigerants, etc.
- The high purity of this gasket sheet makes it excellently suitable for the food and pharmaceutical industry
- TEADIT **TF 1580** is quick and simple to install. The used gasket can be removed easily and without residue.

### Properties:

- Colour: off-white (no dye)
- Size: Sheets of 1500 mm x 1500 mm
- Thickness: 0.5mm up to 3.2mm
- Temperature: -210°C to +260°C
- Chemical resistance: chemically inert against all substances (pH 0-14), including the most aggressive lyes and moderate acids. The only exception are molten alkali metals and elemental fluorine at high temperature and pressure.
- Operating Pressure: 83 bar
- Ageing: TEADIT **TF 1580** is not subject to ageing or weathering. It can be stored indefinitely.
- Safety: TEADIT **TF 1580** is suitable for oxygen applications.

### Approvals:

- TA Luft
- Blow-Out-Test
- Germanischer Lloyd Approval
- DVGW
- BAM (Oxygen)



### P x T diagramm:

The P x T diagram above indicates the service limits considering the simultaneous influence of pressure and temperature (chemical suitability assumed). The green area represents the normal service limits, while the orange coloured area shows the maximum application limits.



**TEADIT®**

sealing for a safer and greener tomorrow

**TEADIT TF 1580**

property	test method	nominal value	parameters
density [g/cm <sup>3</sup> ]	ASTM D 792	2.9	
compressibility [%]	ASTM F 36	10	σ = 34 MPa
recovery [%]	ASTM F 36	40	σ = 34 MPa
compressibility ε KSW [%]	DIN 28090 - 2	9	σ = 20 MPa
recovery ε KRW [%]	DIN 28090 - 2	1.9	σ = 20 MPa
tensile strength [MPa]	ASTM 152	14	room temperature
creep deformation [%]	ASTM F38	11	
stress retention [MPa]	DIN 52913	11	30 N/mm <sup>2</sup> , 150°C, 16h
sealability [ml/h]	ASTM F 37	0.04	0.7 bar
Q min 0,01 [MPa]	EN 13555	< 10	HE 40 bar
Q smin 0,01 [MPa]	EN 13555	< 10	HE 40 bar
Q min 0,001 [MPa]	EN 13555	13	HE 40 bar
Q smin 0,001 [MPa]	EN 13555	< 10	HE 40 bar
Q smax [MPa]	EN 13555	> 240	room temperature
sealability [mg / s • m]	DIN 3535	< 0.015	N <sub>2</sub> , 40 bar, 32 MPa
specific leakage rate L [mbar • l / (s • m)]	VDI 2440 / TA LUFT	5.9 • 10 <sup>-7</sup>	He, 1 bar, 30 MPa

**STOCKED, SUPPORTED AND DISTRIBUTED BY**email: [sales@williamjohnston.co.uk](mailto:sales@williamjohnston.co.uk)[www.williamjohnston.co.uk](http://www.williamjohnston.co.uk)**WILLIAM JOHNSTON  
& COMPANY LIMITED**

Glasgow: 0141 620 1666

Inverness: 01463 238673

**Disclaimer**

Please note, failure to select the correct materials or products we supply ("the Products") may result in damage to plant, equipment or property. In some instances, it may cause death or personal injury. We are not designers and do not give advice about design related matters concerning the Products. We can help and assist with the technical specifications for the Products. In specific applications, particularly where critical conditions exist, we will try to assist you within the limitations of the services that we offer. All information supplied by us is intended as technical co-operation outlining the specifications of the different Products which we supply. To the extent permitted in law, no warranty is given in respect of any information supplied by us. The customer must satisfy themselves as to the suitability of the Products for their intended application and use. The correct fitting of Products is the responsibility of the customer. Your statutory rights remain unaffected. Save in respect of death, personal injury or fraud, our entire liability to you, however arising from the supply of Products shall be limited to the £10M indemnity amount provided by our insurers.