





Glasgow Tel: +44 (0) 141 620 1666 I sales@williamjohnston.co.uk

Inverness Tel: +44 (0) 1463 238 673 www.williamjohnston.co.uk

Data / Specification Sheet • Novus 34

Novus 34 is a superior performance universal compressed sheet material based on a blend of aramid/inorganic fibres and special additives, with high quality nitrile rubber binder system.



AS 34 Manufactured by ONOvus Sealing Group in the EL

#### **Service**

Novus 34, a superior performance material with excellent mechanical properties, it is suitable for many applications including oils, solvents, high pressure steam and gases including oxygen.

#### **Approvals / Compliance**

DIN-DVGW (Gas Industry) NG-5123 AR0822

WRAS Potable Water: Registration No. 1406501

BAM (Oxygen service) up to 90°C and 160 bar Independently tested to Shell specification

MF 94-0960

Complies with BS Specification 7531 Grade X TA-LUFT (in accordance with VDI Guideline

GL Approval cert 37702 - 12HH

## **Availability**

Thickness range: 0.25mm to 6.0mm

Standard sheet sizes:

2.0m x 2.0m

2.0m x 1.5m

2.0m x 1.0m

1.5m x 1.5m

1.5m x 1.0m

Standard roll sizes:

Up to a maximum size of 6.0m x 2.0m


Available with fine mesh mild steel reinforcement: Novus 34 Metallic or gauze mild steel wire reinforcement: Novus 34 GWI.

It can be supplied with anti-stick coating and graphite coating.

### **Typical Physical Properties**

Thickness		1.5mm
Density		1.75g/cc
Tensile Strength	ASTM F152	9-11MPa
Compression	ASTM F36	9%
Recovery	ASTM F36	55% min
Residual Stress	BS 7531 (300°C) DIN 52913	26MPa 32MPa
Gas Leakage	BS 7531	<1.0cc/min
ASTM Oil 1	Thickness increase	1.0%
IRM 903 Oil	Thickness increase	2.5%
ASTM Fuel B	Thickness increase	3.0%

# Novus 34 Pressure/Temperature Limits



Temperature (°C)

Suitable subject to chemical compatibility.

Suitable in some cases but check your application requirements with Flexitallic

Contact the Technical Team for applications with higher temperatures and pressures. Applicable to 1.5mm and below.

The operating temperature of non-asbestos sheet material is related to the thickness of materials selected. Thinner materials give better temperature and pressure properties.

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only, and without liability on the part of the company.