



## Product information

REV2013344

# Stuffing-Box-Packing Type 2024

## Material composition

TEADIT 2024 is an extruded packing made from pure PTFE-fine-powder and a food approved lubricant. Available in round and square cross sections.

Please note: the colour of the actual product might vary from the above image on this data-sheet.

## Properties

Style 2024 is a soft and dense packing. It has a very low coefficient of friction, excellent resistance to gas permeation and is self-lubricating. Style 2024 remains soft and pliable even after long service, which reduces friction on shafts and spindles. Can be used in areas where the naturally dark colour of TEADIT style 2022 is unsuitable, i.e. in the food and pharmaceutical industry.

## Application areas

Suitable for use in pumps, mixers, sliders, valves, but also many static applications. Because of the softness of the packing, it is normally installed with a braided top and bottom ring. Depending on the prevailing pressure and medium, TEADIT styles 2422, 2044, 2005 or 2006 can be recommended for this purpose.

## Application media

Because of the exceptional chemical resistance of pure PTFE, style 2024 can be used with most substances, both liquid and gaseous. Also suitable for use with abrasive and crystallizing media.

## Not suitable for

Alkali metals, fluorine and fluorine compounds at high temperature and pressure, oxygen.

## Benefits

Style 2024 has a very low coefficient of friction and does therefore not damage shafts or spindles. Abrasive or crystallizing particles get embedded in the body of this packing. Can be used with a wide variety of different media, also for static applications.



Temperature:

	- temp	+ temp
(°C)	100	250

Pressure:

	rotating:	reciprocating:	static:
(bar)	10		20

pH: 0-14

density: 1,75

v: (m/s) 4



**WILLIAM JOHNSTON**  
& COMPANY LIMITED

Tel: 0141 620 1666

Fax: 0141 620 1888

[sales@williamjohnston.co.uk](mailto:sales@williamjohnston.co.uk)

[www.williamjohnston.co.uk](http://www.williamjohnston.co.uk)

TEADIT INT. - Rosenheimer Str. 10, 6330 Kufstein, AUSTRIA, Tel.: +43-5372-64020-0, Fax: +43-5372-64020-20, [austria@teadit.eu](mailto:austria@teadit.eu), [www.teadit.eu](http://www.teadit.eu)  
TEADIT Deutschland - Schanzenstr. 35, 51063 Köln, GERMANY, Tel.: +49-221-922 342-0, Fax: +49-221-922 342-22, [germany@teadit.eu](mailto:germany@teadit.eu)

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences TEADIT® has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. TEADIT® does not undertake any liability of any kind whatsoever. Please note: the colour of the actual product might vary from the above image on this data-sheet.