



WILLIAM JOHNSTON **& COMPANY LIMITED**

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

MATERIAL SPECIFICATION.

Compound Reference : 12.7 x 9.5 CR Closed Cell Extrusion		
Material Description	Closed Cell Expanded Neoprene	
Material Specification	ASTM D1056, SCE 42	
Test Method	Specification	Actual Values
SCE 42	Medium Swell	
Compression Deflection	25% Deflection	
	7+/- 2 PSI	6 PSI
Water Absorption	Max Weight 5%	3%
Heat Ageing 7 days @ 70°C		
Deflection Change	+/- 30%	+17%
Compression Set	25% Max	15%
Density	0.6 – 0.7g/cm3	0.65g/cm3

