TECHNICAL DATA





WILLIAM JOHNSTON & COMPANY LIMITED

Inverness +44 (0) 1463 238 673 Head Office +44 (0) 141 620 1666 (8 lines) Ashford +44 (0) 1233 330 766 <u>sales@williamjohnston.co.uk</u> www.williamjohnston.co.uk

PRODUCT NAME

Commercial EPDM 60

DESCRIPTION

THICKNESS (mm) SHEET SIZE (M) FINISH MATERIAL APPLICATION INSERTION CHEMICAL RESISTANCE High grade EPDM suitable for appliations where good ozone and weather resistance is required. Also suitable for some mineral oils 1mm - 25mm

1.4M X 5M, 10M & 20M -thickness dependant Plate/Plate

Plate/Plat

EPDM

General Purpose

No

PLEASE REFER TO OUR CHEMICAL DATA SHEET

SPECIFICATIONS COMPOUND	Values [typical]	1
COLOUR	Black	
COMPOUND	EPDM	
DENSITY [SPECIFIC GRAVITY]	/cm ³ 1.15	
HARDNESS [DEGREES SHORE A]	+/-5 60	
TENSILE STRENGTH	MPa 10	Sec.
ELONGATION AT BREAK	%300	020
MINIMUM TEMPERATURE	°C -30	C I
MAXIMUM TEMPERATURE	°C+130	Therefore
COMPRESSION SET (70°C 22 hour	s) % 30	

As the companies' products are used in multiple applications and as the company has no control over the method of their use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise. Any technical co-operation is given for customers' assistance only and without liability on the part of the company.