TECHNICAL DATA



Inverness +44 (0) 1463 238 673 Head Office +44 (0) 141 620 1666 (8 lines) Ashford +44 (0) 1233 330 766 sales@williamjohnston.co.uk * www.williamjohnston.co.uk

PRODUCT NAME Tan Para (shot-blast)

DESCRIPTION A highly abrasion resistant rubber. Para-natural

> rubber or "pure-gum". Produced from natural latex this material is designed for arduous conditions within mining to include chute lining,

cabinet lining or indeed shot-blast plant lining.

THICKNESS (mm) 1 to 25

1.4 x 5, 10, 20 SHEET SIZE (M)

FINISH Plate/plate

MATERIAL Natural Rubber

APPLICATION High abrasion resistance - shot-blast.

INSERTION NO

CHEMICAL RESISTANCE PLEASE REFER TO OUR CHEMICAL DATA

SHEET

SPECIFICATIONS COMPOUND	Values [typical]
COLOUR	Tan
COMPOUND	Natural Latex
DENSITY [SPECIFIC GRAVITY] g	y/cm ³ 1.02
HARDNESS [DEGREES SHORE A]	+/-5 40
TENSILE STRENGTH	MPa 15.0
ELONGATION AT BREAK	% 600
MINIMUM TEMPERATURE	°C -20
MAXIMUM TEMPERATURE	°C +70
COMPRESSION SET (70°C/22 Hrs)	% 30

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, particularly where critical conditions exist, we suggest you contact us and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products is the responsibility of the customer.