



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673

sales@williamjohnston.co.uk

www.williamjohnston.co.uk

Black Non-Reinforced Diaphragm 100% Premium Grade EPDM 60° shore WJ204

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.15	DIN 53508	1.15
HARDNESS	ASTM D2240	60 ± 5 SH A	DIN 53505	60 ± 5 SH A
TENSILE STRENGTH (MIN)	ASTM D412	1425 PSI	DIN 53504	100 KG/CM2
ELONGATION AT BREAK (MIN)	ASTM D412	300%	DIN 53504	300%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	ASTM D395 METHOD B	30%	DIN 53517	30%
TEAR RESISTANCE (ANGULAR) MIN	ASTM D624	168 LBS/INCH	DIN 53515	30 KG/CM
CHANGE IN PROPERTIES				
HEAT AGEING (72 HRS. AT 70°C)	ASTM D573			
--- HARDNESS (PTS)		+ 3 (MAX)		+ 3 (MAX)
--- TENSILE STRENGTH (%)		+ 10 / - 10		+ 10 / - 10
--- ELONGATION AT BREAK (%)		+ 10 / - 10		+ 10 / - 10
VOLUME SWELL: AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
POLYMER CONTENT (EPDM)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	EXCELLENT		EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30°TO + 130°C		-30°TO + 130°C
COLOUR		BLACK		

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.