



EC1935:2004

Complies with FDA Food Contact Regulation 21
CFR177-2600**WILLIAM JOHNSTON
& COMPANY LIMITED**

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673

sales@williamjohnston.co.uk| www.williamjohnston.co.uk

USP CLASS VI

**Black Silicone Non-Toxic General-Purpose Grade 45° Shore WJ14201
FDA 21 CFR No: 177 – 2600 & EU1935/2004 regulations and USO Class V1 Compliant**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.20 ± 0.05	ASTM D297	1.20 ± 0.05
HARDNESS	DIN 53505	40 ± 5 SH A	ASTM D2240	40 ± 5 SH A
TENSILE STRENGTH (MIN)	DIN 53504	858 PSI	ASTM D412	60 KG/CM2
ELONGATION AT BREAK (MIN)	DIN 53504	200%	ASTM D412	200%
COMPRESSION SET (70° C/24 HRS/25% SET) (MAX)	DIN 53517	40%	ASTM D395 METHOD B	40%
TEAR RESISTANCE (ANGULAR) MIN	DIN 53515	112 LBS/INCH	ASTM D624	20 KG/CM
POLYMER CONTENT (%)		100		100
CHANGE IN PROPERTIES				
HEAT AGEING (72 HRS. AT 100 °C)			ASTM D573	
--- HARDNESS (PTS)		+ 3 (MAX)		+ 3 (MAX)
--- TENSILE STRENGTH (%)		+ 5 / - 5		+ 5 / - 5
--- ELONGATION AT BREAK (%)		+ 5 / - 5		+ 5 / - 5
VOLUME SWELL: AT 70° C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		+ 5%		+ 5%
IRM OIL NO.2		+ 7%		+ 7%
IRM OIL NO.3		+ 25%		+ 25%
CHEMICAL RESISTANCE				
--- OZONE	DIN 53508	EXCELLENT	ASTM D 1149	EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-90 ° TO + 200° C		-90 ° TO + 200° C

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.