



EC1935:2004



Complies with FDA Food Contact Regulation 21 CFR177-2600



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673

sales@williamjohnston.co.uk

www.williamjohnston.co.uk

Off-White Food Quality Neoprene Rubber 65° shore WJ162

US FDA 21 CFR177,2600, EU1935/2004 and USP Class V1Compliant

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.60 ± 0.05	ASTM D297	1.60 ± 0.05
HARDNESS	DIN 53505	65 ± 5 SH A	ASTM D2240	65 ± 5 SH A
TENSILE STRENGTH (MIN)	DIN 53504	716 PSI	ASTM D412	50 KG/CM2
ELONGATION AT BREAK (MIN)	DIN 53504	250	ASTM D412	250
COMPRESSION SET (70 °C/24 HRS/25% SET) (MAX)	DIN ISO 815-1	30	ASTM D395 METHOD B	30
TEAR RESISTANCE (ANGULAR) MIN	DIN 53515	196 LBS/INCH	ASTM D624	35 KG/CM
CHANGE IN PROPERTIES				
HEAT AGEING (72 HRS. AT 70 °C)			ASTM D573	
--- HARDNESS (PTS)		+ 5 (MAX)		+ 5 (MAX)
--- TENSILE STRENGTH (%)		+ 10 / - 15		+ 10 / - 15
--- ELONGATION AT BREAK (%)		+ 10 / - 20		+ 10 / - 20
VOLUME SWELL: AT 70° C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		+ 2 %		+ 2 %
IRM OIL NO.2		+ 15%		+ 15%
IRM OIL NO.3		+ 45%		+ 45%
POLYMER CONTENT (NEOPRENE)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		FAIR		FAIR
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-30° TO + 130° C		-30° TO + 130° C
COLOUR		OFF WHITE		



USP CLASS VI

Extractants	Test Condition	Amount of Extractives (mg/inch ²) 1	Acceptable Limit (mg/inch ²)	Conclusion
Distilled Water	at reflux temp' for 7 hours	<10	<20	Pass
Distilled Water	at reflux temp for succeeding 2 hours of extraction	<1	<1	Pass
n-Hexane	at reflux temp' for 7 hours	<100	<175	Pass
n-Hexane	At reflux temp for succeeding 2 hours of extraction	<4	<4	Pass

Notes:

1. mg/inch² = milligram per square inch
2. °C = degrees Celsius

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.