



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Off-White Natural Rubber to BS1154 Y60 WJ223

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	BS 903: PART A1			1.2
HARDNESS	BS 903: PART A26			60 ± 5 IRHD
TENSILE STRENGTH (KG/CM ²)	BS 903: PART A2			170
ELONGATION AT BREAK (MIN)	BS 903: PART A2			500%
COMPRESSION SET (70 °C/24 HRS/25% SET) (MAX)	BS 903: PART A6			30%
TEAR RESISTANCE (ANGULAR) MIN	BS 903: PART A3			50 KG/CM
ABRASION RESISTANCE				130
CHANGE IN PROPERTIES				
HEAT AGEING (168 HRS. AT 70°C)	BS 903: PART A 19			
--- HARDNESS (PTS)	BS 903: PART A26			+ 5 / -5 (MAX)
--- TENSILE STRENGTH (%)	BS 903: PART A2			-10 (MAX)
--- ELONGATION AT BREAK (%)	BS 903: PART A2			-15(MAX)
POLYMER CONTENT (NATURAL RUBBER)				100%
ADDITIONAL INFORMATION - CHEMICAL RESISTANCE				
--- OZONE	BS 903: PART A 43			NOT RECOMMENDED
--- DILUTE ACIDS AND BASES	BS 903: PART A16			NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES				NOT RECOMMENDED
--- OILS				NOT RECOMMENDED
--- SOLVENTS				NOT RECOMMENDED
TEMPERATURE RANGE				-20° TO + 70°C
COLOUR		OFF WHITE		

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.