



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Black High Abrasion Grade 60° Shore WJ152

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.17±0.05	ASTM D297	1.17±0.05
HARDNESS	DIN 53505	60 ± 5 SH A	ASTM D2240	60 ± 5 SH A
TENSILE STRENGTH (MIN)	DIN 53504	1638 PSI	ASTM D412	115 KG/CM2
ELONGATION AT BREAK (MIN)	DIN 53504	450%	ASTM D412	450%
ABRASION RESISTANCE (MAX)	DIN 53516	120 MM3	ASTM D5963	120 MM3
COMPRESSION SET (70°C/24 HRS/25% COMPRESSION) (MAX)	DIN ISO 815-1	30%	ASTM D395 METHOD B	30%
TEAR RESISTANCE (ANGULAR) MIN	DIN 53515	168 LBS/INCH	ASTM D624	30 KG/CM
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR (72 HRS. AT 70 °C)			ASTM D573	
--- HARDNESS (PTS)		+ 5 (MAX)		+ 5 (MAX)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL: AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-25° TO + 70°C		-25° TO + 70°C
PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
COLOUR			BLACK	

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.

Metroseal, Units 28-30 Purdeys Way, Purdeys Industrial Estate, Rochford, Essex, SS4 1ND
Phone: [+44 \(0\) 1702 548800](tel:+44(0)1702548800) | Fax: [+44 \(0\)1702 549966](tel:+44(0)1702549966) | Email: sales@metroseal.co.uk