



## **WILLIAM JOHNSTON & COMPANY LIMITED**

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673  
[sales@williamjohnston.co.uk](mailto:sales@williamjohnston.co.uk) | [www.williamjohnston.co.uk](http://www.williamjohnston.co.uk)

### Black Neoprene NFF16-101 M2-F3 & UL94-VO Flame Retardent Sheet 65° shore WJ215

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.60 ± 0.05	DIN 53508	1.60 ± 0.05
HARDNESS	ASTM D2240	65± 5 SH A	DIN 53505	65± 5 SH A
TENSILE STRENGTH (KG/CM2)	ASTM D412	710 PSI	DIN 53504	50 KG/CM2
ELONGATION AT BREAK (MIN)	ASTM D412	200%	DIN 53504	200%
TEAR RESISTANCE (ANGULAR) MIN	ASTM D624	90 LBS/INCH	DIN 53515	16 KG/CM
POLYMER CONTENT				100%
CHANGE IN PROPERTIES				
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	GOOD		GOOD
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30 C + 130 C		-30 C + 130 C
FIRE & SMOKE				
FIRE - CLASSIFICATION	NF F16-101	MEETS M2 REQUIREMENT	NFF 16-101	MEETS M2 REQUIREMENT
SMOKE CLASSIFICATION				
SMOKE DENSITY	NF F16-101	MEETS F3 REQUIREMENT		
SMOKE TOXICITY	NF F16-101	MEETS F3 REQUIREMENT		
COLOUR		BLACK		

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.