

Glasgow Tel: +44 (0) 141 620 1666 I Inverness Tel: +44 (0) 1463 238 673 <u>sales@williamjohnston.co.uk</u> I <u>www.williamjohnston.co.uk</u>

Black Neoprene to BS2752 C70 WJ182

PROPERTIES.	TEST METUOD	VALUES
PROPERTIES	TEST METHOD	METRIC UNITS
SPECIFIC GRAVITY	BS 903: PART A1	1.40
HARDNESS	BS 903: PART A26	70 ± 5 IRHD
TENSILE STRENGTH (KG/CM2)	BS 903: PART A2	130
ELONGATION AT BREAK (MIN)	BS 903: PART A2	300%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	BS 903: PART A6	25%
TEAR RESISTANCE (ANGULAR) MIN	BS 903: PART A3	40 Kg/cm
RESISTANCE TO ACCELERATED AGEING- 168HRS AT 70°C	BS 903: PART A19	
HARDNESS (Pts)	BS 903: PART A26	+ 7 (MAX)
TENSILE STRENGTH (%)	BS 903: PART A2	-12 (MAX)
ELONGATION AT BREAK (%)	BS 903: PART A2	-20 (MAX)
VOLUME SWELL: AT 40°C FOR 24 HRS/IN	BS 903: PART A16	
FUEL B		+ 70% (MAX)
RESISTANCE TO LOW TEMPERATURE AT - 40°C	BS 903: PART A13	MEETS REQUIREMENTS
ADHESION TO AND CORROSION OF METALS	BS 903: PART A 37	MEETS REQUIREMENTS
POLYMER CONTENT (NEOPRENE)		100%
ADDITIONAL INFORMATION -		
CHEMICAL RESISTANCE		
OZONE	BS 903: PART A 43	GOOD
DILUTE ACIDS AND BASES	BS 903: PART A16	GOOD
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED
MINERAL OILS - PARAFINNIC & NAPHTHANIC HC		GOOD
MINERAL OILS - AROMATIC HC		FAIR
ANIMAL/VEGETABLE OIL		GOOD
SOLVENTS		FAIR
TEMPERATURE RANGE		-30° TO + 120° C
COLOUR	BLACK	

VOLUME SWELL DATA		
RESISTANCE TO LIQUIDS	BS ISO 1817, 24	-0
VOLUME CHANGE (%) AFTER IMMERSION IN LIQUID B	BS ISO 1817, 24 ⁰ / ₋₂ h at (40±1) °C	+70
RESISTANCE TO ACCELERATED AGEING	PART A19, AIR-OVEN METHOD A, (168±2)h, (70±1)°C	-0
CHANGE IN HARDNESS DEGREES (IRHD)	PART A26, METHOD N, MEASUREMENTS BEFORE AND AFTER AGEING ON THE SAME 2 PLIES EACH 2.00MM THICK	+7
MAXIMUM CHANGE IN TENSILE STRENGTH (% OF ORIGINAL VALUE)	PART A2, TYPE 1 OR TYPE 2 DUMBBELLS	-12
MAXIMUM CHANGE IN ELONGATION AT BREAK (% OF ORIGINAL VALUE)	PART A2, TYPE 1 OR TYPE 2 DUMBBELLS	-20

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.