



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Blue Metal Detectable Neoprene WJ168

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.50 ± 0.05	ASTM D297	1.50 ± 0.05
HARDNESS	DIN 53505	65 ± 5 SH A	ASTM D2240	65 ± 5 SH A
TENSILE STRENGTH (MIN)	DIN 53504	1990PSI	ASTM D412	140 KG/CM2
ELONGATION AT BREAK (MIN)	DIN 53504	600%	ASTM D412	600%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	DIN 53517	50%	ASTM D395 METHOD B	50%
POLYMER CONTENT (%)		100		100
TEAR RESISTANCE (ANGULAR) MIN	DIN 53515	170 LBS/INCH	ASTM D624	30 KG/CM
CHANGE IN PROPERTIES AFTER HEAT AGEING (72 HRS. AT 70 °C)			ASTM D573	
--- HARDNESS (PTS)		+ 5 (MAX)		+ 5 (MAX)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 30		+ 10 / - 30
VOLUME SWELL : AT 70°C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		+18%		+18%
IRM OIL NO.2		+23%		+23%
IRM OIL NO.3		+60%		+60%
POLYMER CONTENT (NEOPRENE)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE		GOOD	ASTM D 1149	GOOD
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		FAIR		FAIR
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-25° TO + 120° C		-25° TO + 120° C
COLOUR		BLUE		

Extraction Data Test Results

Test Name: Determination of Amount of Extractives Method : With reference to US FDA 21 CFR 177.2600

For use in contact with aqueous food:

Extractants	Test Condition	Result (MG/INCH ²)	Reporting Limit MG/INCH ²	Permissible Limit MG/INCH ²
Distilled Water	Reflux Temperature for 7 Hours	<0.1	0.1	20
	Succeeding 2 hours of extraction	<0.1	0.1	1
Comment	--	PASS	--	--

For use in contact with fatty foods

Extractants	Test Condition	Result (MG/INCH ²)	Reporting Limit MG/INCH ²	Permissible Limit MG/INCH ²
n-Hexane	Reflux Temperature for 7 Hours	<0.1	0.1	175
	Succeeding 2 hours of extraction	<0.1	0.1	4
Comment	--	PASS	--	--

Note MG/INCH² = Milligram per square inch

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.