



## WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673  
[sales@williamjohnston.co.uk](mailto:sales@williamjohnston.co.uk) | [www.williamjohnston.co.uk](http://www.williamjohnston.co.uk)

### Black NBR Nitrile Coated Nylon Diaphragm Sheeting 70 Shore to BS2751 BA70 – 0.50mm WJ195CO

Properties	Test Method	Values FPS Units
Volume Swell: At 40°C for 24hrs/in		
Fuel B (Max)	BS 903: Part A16	+25%
Resistance to low temperature in °C at which the stiffness shall not exceed 70MPA	BS903: Part A13	-25
Adhesion to and corrosion of metals at 70°C/168 hrs	BS 903: Part A37	MEETS REQUIREMENTS
Polymer Content (Nitrile)		100%
Additional Information		
Chemical Resistance		
Ozone	BS 903: Part A43	FAIR
Dilute Acids and Bases	BS 903: Pat A16	GOOD
Concentrated Acids and Bases		NOT RECOMMENDED
Mineral Oil/Petroleum		EXCELLENT
Solvents		FAIR
LPG/CNG		GOOD
Water		GOOD
Volume Swell: At 70°C for 72 hrs/in		
IRM / ASTM Oil No. 1		- 3%
IRM / ASTM Oil No. 2		- 2%
IRM / ASTM Oil No. 3		+ 10%
Nitrile Rubber Coated Fabric in Black for Diaphragm Sheet – 0.50mm		
Elastomer Characteristics	Value	Test Method
Elastomer	NBR Nitrile Rubber	BS2751 BA70
Hardness	70 ± 5 SH A	DIN 53505
Colour	Black	
Fabric Characteristics		
Fabric	10056	
Weight	180 GSM	
Thickness	0.23mm	
Coated Fabric Characteristics		
Thickness	0.50 ± 0.05	
Weight	650 ± 50	ASTM D-751 IS-7016 (Pt-I)
Tensile Strength kg/50mm	Warp	ASTM D-751 IS 7016-Part II ISO-1421
	Weft	
Elongation at Break	Warp	30% (max)
	Weft	
Adhesion (Peel Strength) kg/25mm	5kg	ASTM D-751
Temperature range	-25° to +110°C	

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.