



WILLIAM JOHNSTON & COMPANY LIMITED

Glasgow Tel: +44 (0) 141 620 1666 | Inverness Tel: +44 (0) 1463 238 673
sales@williamjohnston.co.uk | www.williamjohnston.co.uk

Black Nitrile to BS2751 BA60 WJ191

PROPERTIES	TEST METHOD	VALUES
		METRIC UNITS
DENSITY (Mg/m ³)	BS 903: PART A1	1.2 ± 0.02
HARDNESS	BS903: PART A26	60 (+5-4) IRHD
TENSILE STRENGTH (MIN)	BS 903: PART A2	8.5 Mpa
ELONGATION AT BREAK (MIN)	BS 903: PART A2	400%
COMPRESSION SET (70°C/24 HRS/25% SET) (MAX)	BS 903: PART A6	20%
TEAR RESISTANCE (ANGULAR) MIN	BS 903: PART A3 (Z)	45 Kg/cm
RESISTANCE TO ACCELERATED AGEING – 168 HRS AT 70°C	BS 903: PART A19	
--- HARDNESS (Pts)	BS 903: PART A26	+ 10 (MAX)
--- TENSILE STRENGTH (%)	BS 903: PART A2	-10 (MAX)
--- ELONGATION AT BREAK (%)	BS 903: PART A2	-35 (MAX)
VOLUME SWELL: AT 40°C FOR 24 HRS/IN	BS 903: PART A16	
FUEL B (MAX)		+25%
RESISTANCE TO LOW TEMPERATURE IN °C AT WHICH THE STIFNESS SHALL NOT EXCEED 70 MPA	BS 903: PART A13	-25
ADHESION TO AND CORROSION OF METALS AT 70°C / 168 HRS	BS 903: PART A 37	MEETS REQUIREMENTS
POLYMER CONTENT (NITRILE)		100%
ADDITIONAL INFORMATION -		
CHEMICAL RESISTANCE		
--- OZONE	BS 903: PART A 43	FAIR
--- DILUTE ACIDS AND BASES	BS 903: PART A16	GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED
--- MINERAL OIL/PETROLEUM		EXCELLENT
--- SOLVENTS		FAIR
TEMPERATURE RANGE		-25° to +120°C
COLOUR	BLACK	
VOLUME SWELL: AT 70 C FOR 72 HRS/IN		VALUES
IRM / ASTM OIL NO.1		- 3 %
IRM / ASTM OIL NO.2		- 2%
IRM / ASTM OIL NO.3		+ 10%

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.