

Black Commercial Premium Quality 1 ply Insertion NR SBR 70° shore WJ126

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.5	DIN 53508	1.5
HARDNESS	ASTM D2240	70 ± 5 SH A	DIN 53505	70 ± 5 SH A
TENSILE STRENGTH (MIN)	ASTM D412	426 PSI	DIN 53504	30 KG/CM2
ELONGATION AT BREAK (MIN)	ASTM D412	200%	DIN 53504	200%
TEAR RESISTANCE (ANGULAR) MIN	ASTM D624	90 LBS/INCH	DIN 53515	16 KG/CM
CHANGE IN PROPERTIES				
HEAT AGEING (72 HRS. AT 70 °C)	ASTM D573			
HARDNESS (PTS)		+ 5 (MAX)		+ 5 (MAX)
TENSILE STRENGTH (%)		+ 10 / -25		+ 10 / -25
ELONGATION AT BREAK (%)		+ 10 / -25		+ 10 / -25
VOLUME SWELL: AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-20° TO + 70° C		-20° TO + 70° C
COLOUR		BLACK		BLACK
APPREANCE		1PLY COTTON 22+/-5 GSM FABRIC		

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.