

White Food Quality NR / SBR 60° shore WJ136

Approved to: US FDA21 CFR177,2600 & EU1935/2004 and USP Class 1 V1 Compliant

| | TEOT | VALUES | | VALUES |
|--|------------------|-----------------|-----------------------|-----------------|
| PROPERTIES | TEST METHOD | FPS UNITS | TEST METHOD | METRIC UNITS |
| SPECIFIC GRAVITY | DIN 53508 | 1.5 ± 0.05 | ASTM D297 | 1.5 ± 0.05 |
| HARDNESS | DIN 53505 | 60 ± 5 SH A | ASTM D2240 | 60 ± 5 SH A |
| TENSILE STRENGTH (MIN) | DIN 53504 | 1140 PSI | ASTM D412 | 60 KG/CM2 |
| ELONGATION AT BREAK (MIN) | DIN 53504 | 200% | ASTM D412 | 200% |
| COMPRESSION SET (70°C/24 HRS/25% COMPRESSION) (MAX) | DIN ISO 815-1 | 40% | ASTM D395 METHOD B | 40% |
| POLYMER CONTENT | | NA | | NA |
| TEAR RESISTANCE (ANGULAR) MIN | DIN 53515 | 112 LBS/INCH | ASTM D624 | 20 KG/CM |
| CHANGE IN PROPERTIES AFTER | | | | |
| HEAT AGEING FOR (72 HRS. AT 70 °C) | | | ASTM D573 | |
| HARDNESS (PTS) | | + 5 (MAX) | | + 5 (MAX) |
| TENSILE STRENGTH (%) | | + 10 / 15 | | + 10 / 15 |
| ELONGATION AT BREAK (%) | | + 10 / 15 | | + 10 / 15 |
| VOLUME SWELL: AT 70°C FOR 72 HRS | | | ASTM D 471 | |
| IN IRMOIL NO.1 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| IN IRMOIL NO.2 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| IN IRMOIL NO.3 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| CHEMICAL RESISTANCE | | | | |
| OZONE | | NOT RECOMMENDED | ASTM D 1149 | NOT RECOMMENDED |
| DILUTE ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| CONCENTRATED ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| OILS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| SOLVENTS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| TEMPERATURE RANGE | | -30 ° TO + 70°C | | -30 ° TO + 70°C |
| COLOUR | | OFF-WHITE | | OFF-WHITE |

| | TEST RESULTS: MIGRATION DATA | | | | | | |
|--|--|-------------------|--|----------------------------|--|--|--|
| | (TEST NO. 1-I) SENSORY VERIFICATION OF ODOUR/SMELL | | | | | | |
| (TEST NO. 1-I) SE | ENSORY VERIFICA | FION OF ODOUR/SME | LL TEST SPECIFICATION(S)/REGU | LATION(S): REGULATION (EC) | | | |
| NO. 1935/2004 | & COUNCIL OF EU | | RESAP (2004) 4 ON RUBBER PROD | UCTS INTENDED TO COME | | | |
| | | | T WITH FOODSTUFFS. | | | | |
| | | | DOPTED: DIN 10955:2004. | | | | |
| | TE | | SED: DISTILLED WATER. 0 0C OR REFLUX FOR 4 HOURS. | | | | |
| | | | | | | | |
| COMPONENT NO. | COMPACT NOT CONTRACT OF CONTRACT NOT CONTRACT OF CONTRACT. | | | | | | |
| A | RATING | 0 | LESS THAN 2.5 | PASS | | | |
| A RATING 0 LESS THAN 2.5 PASS Note: (INTERMEDIATE GRADES ARE ALLOWED) 0 = NO PERCEPTIBLE DIFFERENCE IN ODOUR. 1 = JUST PERCEPTIBLE DIFFERENCE IN ODOUR (STILL DIFFICULT TO DEFINE). 2 = SLIGHT DIFFERENCE IN ODOUR. 3 = MARKED DIFFERENCE IN ODOUR. 4 = STRONG DIFFERENCE IN ODOUR | | | | | | | |

| | (TEST NO. 1-II) SENSORY VERIFICATION OF TASTE | | | | | | | |
|--|---|---|---------------|------|--|--|--|--|
| TEST SPECIFICATION(S)/REGULATION(S): REGULATION (EC) NO. 1935/2004 & COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFFS. TEST METHOD ADOPTED: DIN 10955:2004. SIMULANT(S) USED: DISTILLED WATER. TEST CONDITION(S): 100°C OR REFLUX FOR 4 HOURS. | | | | | | | | |
| COMPONENT NO. | ENT NO. TEST PARAMETERS RESULT (GRADE) COMPLIANCE REQUIREMENT/LIMIT MAX. CONCLUSION (PASS/FAIL) (REFER REMARK 3 ON PAGE NO.2) | | | | | | | |
| А | RATING | 0 | LESS THAN 2.5 | PASS | | | | |
| Note: (INTERMEDIATE GRADES ARE ALLOWED) 0 = NO PERCEPTIBLE DIFFERENCE IN TASTE. 1 = JUST PERCEPTIBLE DIFFERENCE IN TASTE (STILL DIFFICULT TO DEFINE). 2 = SLIGHT DIFFERENCE IN TASTE. 3 = MARKED DIFFERENCE IN TASTE. 4 = STRONG DIFFERENCE IN TASTE. | | | | | | | | |

| | (TEST NO. 2) OVERALL MIGRATION | | | | | | | |
|------------------------|---|------------------------------------|----------|------|--|--|--|--|
| | TEST SPECIFICATION(S)/REGULATION(S): COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFFS. TEST METHOD(S) ADOPTED: WITH REFERENCE TO EN 1186-3:2002 (FOR 3 % ACETIC ACID) & EN 1186-14:2002 (FOR 95 % ETHANOL AND ISO-OCTANE); SIMULANTS USED: REFER BELOW. TEST CONDITION(S): REFER BELOW (NOTE: TESTS CONDUCTED UNDER REPEAT-USE CONDITIONS); | | | | | | | |
| S.NO. | S.NO. SIMULANT USED TEST COMPONENT NO. RESULT (MG/KG) | | | | | | | |
| 1 | 3 % ACETIC ACID | 100 °C OR REFLUX FOR 4 HOURS | A | ND | | | | |
| 2 | 95 % ETHANOL | 60 °C FOR 6 HOURS | Δ | | | | | |
| 3 | ISO- OCTANE | 60 °C FOR 4 HOURS | А | ND | | | | |
| | OVERALL | CONCLUSION (PA | SS/FAIL) | Pass | | | | |
| | LIMIT OF QUANTIFICATION: 12.0 MG/KG | | | | | | | |
| (2) °C DI (3) "%" D | Note (1) "MG/KG" DENOTES MILLIGRAM PER KILOGRAM: (2) °C DENOTES DEGREES CELCIUS. (3) "%" DENOTES PER CENT. (4) "ND" DENOTES NOT DETECTED | | | | | | | |

| | (TEST NO. 3) Specific migration of primary aromatic amines | | | | | | | |
|--|---|--|--|--|--|--|--|--|
| TEST SPECIFICATION(S)/REGULATION(S): COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFFS. TEST METHOD(S) ADOPTED: WITH REFERENCE TO EN 13130-1:2004 FOLLOWED BY ANALYSIS USING UV VISIBLE SPECTROPHOTOMETER. SIMULANT(S) USED: 3 % ACETIC ACID. TEST CONDITION(S): 100 °C OR REFLUX FOR 4 HOURS (UNDER REPEAT-USE CONDITIONS); EQUIPMENT(S) USED: UV VISIBLE SPECTROPHOTOMETER. | | | | | | | | |
| COMPONENT NO. | OUANTIFICATION REQUIREMENT/TIMIT CONCLUSION (PASS/FAIL) | | | | | | | |
| A | A ND 0.01 SUM OF PRIMARY AROMATIC AMINES SHALL BE LESS THAN 0.01 MG/KG | | | | | | | |
| Note: (1) "MG/KG" DENOTES MILLIGRAM PER KILOGRAM: (2) °C DENOTES DEGREES CELCIUS. (3) "%" DENOTES PER CENT. (4) "ND" DENOTES NOT DETECTED. (5) "UV" DENOTES ULTRA-VIOLET | | | | | | | | |

| | (TEST NO. 4-I) SPECIFIC MIGRATION OF PHTHALATES | | | | | | | |
|------------------|---|--|----|-----|--------------------------|------|--|--|
| | TEST SPECIFICATION(S)/REGULATION(S): COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFF. TEST METHOD(S) ADOPTED: WITH REFERENCE TO EN 13130-1:2004 FOLLOWED BY ANALYSIS USING GC MS; SIMULANT(S) USED: 95 % ETHANOL. TEST CONDITION(S): 60 °C FOR 6 HOURS (UNDER REPEAT-USE CONDITIONS). EQUIPMENT(S) USED: GC MS (GAS CHROMATOGRAPHY MASS SPECTROMETER). | | | | | | | |
| S.NO | NO PARAMETER CAS NO. RESULT (MG/KG) - COMPONENT NO. A LIMIT OF COMPLIANCE REQUIREMENT/LIMIT MAX. CONCLUSION (PASS/FAIL) (REFER REMARK 3 ON PAGE NO.2) | | | | | | | |
| 1 | BENZYLBUTYL PHTHALATE (BBP) | 85- 68-7 | ND | 0.3 | NOT TO EXCEED 6 MG/KG | PASS | | |
| 2 | DIETHYLHEXYL PHTHALATE (DEHP) | 117- 81-7 | ND | 0.3 | NOT TO EXCEED 3 MG/KG | PASS | | |
| 3 | DIBUTYL PHTHALATE (DBP) | HALATE 84- ND 0.3 NOT TO EXCEED 3 PASS | | | | | | |
| 4 | 4 DICYCLOHEXYL PHTHALATE (DCHP) 84- 61-7 ND 0.3 NOT TO EXCEED 6 MG/KG PASS | | | | | | | |
| 5 | DIETHYL PHTHALATE (DEP)84- 66-2ND0.3NOT TO EXCEED 12 MG/KGPASS | | | | | | | |
| | OVERALL CONCLUSION (PASS/FAIL) PASS | | | | | | | |
| (2)″NE (3) °C | Note (1) "MG/KG" DENOTES MILLIGRAM PER KILOGRAM: (2)"ND" DENOTES NOT DETECTED. (3) °C DENOTES DEGREES CELCIUS. (4) "%" DENOTES PERCENTAGE. | | | | | | | |

| | (Test No. 4-ii) Specific migration of phthalates Test Specification(s)/Regulation(s): Council of Europe Resolution ResAP (2004) 4 on rubber products intended to come into contact with foodstuff. Test method(s) adopted: With reference to EN 13130-1:2004 followed by analysis using GC MS; Simulant(s) used: Iso-octane. Test Condition(s): 60°C for 4 hours (under repeat-use conditions). | | | | | | | |
|--------|---|----------|----|-----|--------------------------|------|--|--|
| S. No. | Equipment(s) used: GC MS (Gas Chromatography Mass Spectrometer). S. No. Parameter CAS No. Result (mg/kg) - Component No. A Limit of Quantification (mg/kg) Compliance Requirement / Limit Max. Conclusion (Pass/Fail) | | | | | | | |
| 1 | Benzylbutyl phthalate (BBP) | 85-68-7 | ND | 0.3 | Not to exceed 6 mg/kg | Pass | | |
| 2 | Diethylhexyl phthalate (DEHP) | 117-81-7 | ND | 0.3 | Not to exceed 3 mg/kg | Pass | | |
| 3 | Dibutyl phthalate (DBP) 84-74-2 ND 0.3 Not to exceed 3 mg/kg | | | | | Pass | | |
| 4 | Dicyclohexyl phthalate (DCHP) 84-61-7 ND 0.3 Not to exceed 6 mg/kg | | | | | | | |
| 5 | 5 Diethyl phthalate (DEP) 84-66-2 ND 0.3 Not to exceed 12 mg/kg Pass | | | | | | | |
| | Overall Conclusion (Pass/Fail) Pass | | | | | | | |
| | lote: "mg/kg" denotes milligram per kilogram: (2) "ND" denotes Not Detected; (3) °C denotes degrees Celsius; (4) "%" denotes ercentage. | | | | | | | |

| | (TEST NO. 5) Migration of N-Nitrosamines & N-Nitrosatable substances | | | | | | |
|---|--|--|--|--|--|--|--|
| TEST SPECIFICATION(S)/REGULATION(S): COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFF. TEST METHOD ADOPTED: BASED ON BS EN 12868:1999. EQUIPMENT(S) USED: GAS CHROMATOGRAPHY MASS SPECTROMETER (GC MS). | | | | | | | |
| TEST PARAMETER COMPONENT NO. TEST RESULT (MG/KG) LIMIT OF QUANTIFICATION (MG/KG) COMPLIANCE CONCLUSION (PASS/FAIL) | | | | | | | |
| MIGRATION OF N- NITROSAMINE S | A ND 0.01 SHALL BE LESS THAN PASS | | | | | | |
| MIGRATION OF N- NITROSATABLE SUBSTANCESAND0.1SHALL BE LESS THAN 0.1 MG/KGPASS | | | | | | | |
| Note: (1) "ND" denotes NOT Detected. (2) mg/kg denotes Milligram per Kilogram | | | | | | | |

| (TEST NO. 6) SPECIFIC MIGRATION OF BUTADIENE (1,3-BUTADIENE) (CAS NO. 106-99-0) | | | | | | | | |
|---|--|-----------|---------------------------------|------|--|--|--|--|
| TEST SPECIFIC | TEST SPECIFICATION(S)/REGULATION(S): COUNCIL OF EUROPE RESOLUTION RESAP (2004) 4 ON RUBBER PRODUCTS INTENDED TO COME INTO CONTACT WITH FOODSTUFF; | | | | | | | |
| 13130- 15:2005 | TEST METHOD(S) ADOPTED: WITH REFERENCE TO EN 13130-1:2004 FOLLOWED BY ANALYSIS AS PER DD CEN/TS 13130- 15:2005; SIMULANTS USED: 3 % ACETIC ACID; TEST CONDITION(S): 100 °C OR REFLUX FOR 4 HOURS (UNDER REPEAT-USE CONDITIONS); EQUIPMENT(S) USED: GAS CHROMATOGRAPHY MASS SPECTROMETER (GC MS); | | | | | | | |
| COMPONENT NO. | DETECTION REQUIREMENT/TIMU CONCLUSION (PASS/FAIL) | | | | | | | |
| А | ND | 0.2 MG/KG | SHALL BE LESS THAN 0.02MG/KG | PASS | | | | |
| Note: (1) "MG/KG" DENOTES MILLIGRAM PER KILOGRAM: (2) °C DENOTES DEGRESS CELCIUS. (3) "%" DENOTES PERCENTAGE (4) DENOTES NOT DETECTED END OF TEST REPORT | | | | | | | | |

Failure to select the correct materials or products can result in damage to plant and equipment and personal injury. In specific applications, where critical conditions exist, we suggest you contact us, and we will consider with you the most suitable material or product. However, information supplied by William Johnston & Company Limited is intended only as technical co-operation and as a guide to the various uses of different products. No warranty is given in respect of information or recommendations by William Johnston & Company Limited which are only given for guidance and without any guarantee. The customer must satisfy themselves on the suitability of the material or product for the intended purpose. The correct fitting of products particularly is the responsibility of the customer.