

9 Spiersbridge Terrace, Thornliebank Industrial Estate, Thornliebank, Glasgow. G46 8JH

Tel 0141 620 1666, Fax 0141 620 1888

PVC NITRILE CLASS O			
COMPOSITION		FLEXIBLE CLOSED CELL P.V.C NITRILE ELASTOMER	
COLOUR		BLACK/DULL GREY	
PRODUCT DATA			
TYPE-GRADE CONDITION	SOFT - N	1EDIUM	
TEMPERATURE RANGE °C	2		-50 TO +116
WATER VAPOUR PERMEABILITY	BS4370 PA	RT 2 1973	U > 5,000 0.13/ugm/ (N.h)
WATER ABSORPTION			0.9%
(BY VOLUME 28 DAYS)			AVERAGE
THERMAL CONDUCTIVITY: MEAN	BS874 PA	RT 2 1986	0.037W (m.k)
FIRE RESISTANCE:	A	Ö	1
BS476 – Part 6	<u>_</u>	20	CLASS O
BS476 – Part 7			CLASS 1
ASTM D635	-00		SELF EXTINGUISHING
UL94			V-0 (Yellow Carded)
JIS K6911	e ^o		5VA
NOISE REDUCTION	1	ö	< 30Db (A)
SPECIAL CHARACTERISTICS			
THERMAL INSULATOR (SEALING) MATERIAL			
RESISTANCE			
WEATHER & UV RESISTANCE	GOOD		
OZONE: ASTM D1171	EXCELLENT	•	
CHEMICAL:	GOOD		
ODOUR	N/A		
MILDEW	NO FUNGA	L GROWTH	
OIL & GREASE	GOOD		
ADDITIONS			
CAN BE SUPPLIED WITH VARIOUS SELF ADHESIVE BACKED TAPES DEPENDANT ON APPLICATION ON ONE OR BOTH SIDES			
PROCESSING			
WIDTH - SUPPLIED IN COILS FROM 5MM WIDE UP TO AND INCLUDING 1000mm WIDE			
THICKNESS - VARIOUS DEPENDANT ON YOUR REQUIREMENTS			
LENGTH - CAN BE OFFERED CONTINUOUS			
SHEET - 1.83M X 1M X VARIOUS THICKNESSES			
DIE CUT PARTS - LOW TO HIGH VOLUME DIE CUT PARTS – WITH/WITHOUT ADHESIVE BACKING			
CAD CUT PARTS - TO YOUR DESIGN OR .DXF FILE			
HAPPY TO WORK WITH YOU ON SAMPLES OR PARTS TRIALLING			